

Sulphide Test 1	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	3.5	4,633	2.10	1.65	1.22	58.60	77.44	24.33	53.03
Rougher Con 1-2	9.9	2,262	0.87	0.81	0.53	79.98	90.02	33.37	63.95
Rougher Con 1-3	13.7	1,817	0.65	0.65	0.40	89.15	93.07	37.26	66.78
Rougher Con 1-4	17.1	1,492	0.53	0.58	0.33	91.67	94.77	41.22	69.32

Sulphide Test 2	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	0.2	37,244	11.51	15.38	9.88	33.63	28.83	15.32	29.90
Rougher Con 1-2	2.2	9,585	2.34	3.00	1.96	78.31	53.12	27.01	53.57
Rougher Con 1-3	5.1	4,676	1.18	1.58	0.98	86.62	60.87	32.37	60.89
Rougher Con 1-4	8.2	3,038	1.06	1.09	0.64	90.65	88.01	36.00	64.23

Sulphide Test 3	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	9.7	2,379	0.81	0.71	0.52	82.14	81.24	27.96	61.56
Rougher Con 1-2	14.1	1,786	0.60	0.57	0.39	90.01	87.40	32.63	67.61
Rougher Con 1-3	17.7	1,449	0.48	0.49	0.32	91.55	88.22	34.91	69.38
Rougher Con 1-4	35.0	760	0.26	0.34	0.18	94.67	91.94	48.32	77.45

Sulphide Test 4	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	0.8	22,666	7.91	5.85	3.15	66.13	65.66	19.65	31.08
Rougher Con 1-2	2.1	11,250	3.72	3.00	2.12	86.32	81.28	26.45	54.94
Rougher Con 1-3	2.8	8,754	2.84	2.37	1.67	90.63	83.53	28.24	58.52
Rougher Con 1-4	4.4	5,876	1.89	1.64	1.13	94.06	86.03	30.13	61.11

Oxide Test 1	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	1.6	13,225	2.69	1.29	0.60	64.72	30.37	9.74	15.16
Rougher Con 1-2	4.2	6,347	1.39	0.74	0.32	81.81	41.45	14.63	21.49
Rougher Con 1-3	9.1	3,055	0.74	0.46	0.18	85.48	47.69	19.79	26.60
Rougher Con 1-4	20.8	1,401	0.40	0.32	0.12	89.51	58.43	31.22	37.87

Oxide Test 2	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	0.2	39,302	14.36	6.31	2.95	24.29	19.69	6.08	9.06
Rougher Con 1-2	0.9	23,392	5.51	2.31	1.18	67.81	35.41	10.44	16.99
Rougher Con 1-3	2.0	13,095	4.04	1.33	0.70	82.79	56.70	13.07	22.08
Rougher Con 1-4	2.3	11,709	3.77	1.20	0.64	85.45	61.01	13.68	23.07

Oxide Test 3	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	1.3	13,530	3.35	3.18	0.95	51.52	29.94	19.60	18.95
Rougher Con 1-2	4.2	6,330	1.57	1.27	0.41	80.02	46.52	25.99	27.27
Rougher Con 1-3	13.2	2,117	0.58	0.52	0.17	84.89	54.29	33.63	35.16
Rougher Con 1-4	26.3	1,124	0.34	0.34	0.11	89.54	64.50	43.94	46.26

Oxide Test 4	Mass	Cumulative Grade				Cumulative Recovery			
	(%)	Ag	Pb	S	Cu	Ag	Pb	S	Cu
Rougher Con 1	0.6	32,000	6.46	3.13	1.36	55.25	27.29	8.81	12.41
Rougher Con 1-2	2.0	12,725	2.72	1.85	0.59	79.30	41.50	18.86	19.28
Rougher Con 1-3	2.6	10,529	3.00	1.58	0.51	84.18	58.73	20.57	21.44
Rougher Con 1-4	3.2	8,809	2.89	1.33	0.45	87.16	69.89	21.47	23.63

Table 19: Sulphide and oxide Flotation Tests Summary results